



PRODUCT INFORMATION

PF13/45DB M HS Transp.

Article number: 3650801

Description of the Product: Film backing: Polyethylene film
Color: transparent
Adhesive type: Acrylic

Technical data: Thickness: 45 µm (QMP 21)*
Adhesion to stainless - steel: 1.0 +/- 0.2 N/cm (QMP 02)*

Application: The film **PF13/45DB M HS Transp.** is recommended for the protection of sensitive surfaces against dirt and damage during storage, transportation and processing. When applied correctly, the film can be removed without leaving any residues. As per our actual knowledge, the film is suitable for e.g. the following surfaces:

- Painted metal (PVDF, polyester...)
- Plastic sheets (PVC, PC, melamine)

Application conditions: - The surface must be free from oil, fat, dust and solvents
- Room temperature (> 10°C and < 40°C)

Resistance: - Against moisture: Good
- Against oil: Moderate
- Against solvents: Moderate
- Against UV: 3-6 months**

Storage conditions of rolls: - Room temperature (> 10°C and < 40°C)
- Storage time max. 6 months after date of production -
- No direct exposure to sunlight and moisture

* QMP: POLIFILM Protection internal method of measurement

** 3-6 months UV-resistance according to Western European climate which corresponds to a 150-300 hrs. QUV test (QMP 48)

Note:

The data and recommendations are given in good faith, on the basis of practical experience, but without warranty. The aforementioned characteristics are valid for standard surfaces. The film's performance may differ on specific surfaces, when applied under specific conditions. For this reason, it is highly recommended to the customer to carry out own tests under own specific conditions. Subject to technical changes.

All claims regarding liability and responsibility are based on the individual arrangements in the contract agreement, if not superseded by legal regulations.

Status: 09.06.2014